





# **TECHNICAL DATA SHEET**

DYNAPLUS FAST CURE GASKET MAKER PART NOS. 143358, 143359

# **TYPICAL PROPERTIES**

These values are not intended for use in preparing specifications

TypeAppearance/Color	
Specific Gravity	
Extrusion Rate (g/min)	125
Slump (in)	0
Skin Over Time (min)	3
Tack Free Time (min)	12
Shore "A"	35
Tensile Strength (psi)	350
Elongation (%)	
Modulus (psi)	120
VOC (g/L)	39
Operating Temperature	
	(-65°C to 260°C)

## DESCRIPTION

**Dynatex®** DynaPlus Fast Cure Gasket Maker is a neutral cure form-in-place rubber gasket maker. It has been uniquely formulated to provide a guicker cure time and excellent adhesion, to allow a quicker return to service. In addition to these properties *Dynatex® DynaPlus* Fast Cure Gasket Maker formulation increases its resistance to water, anti-freeze, transmission fluid and engine oil. It is capable of peak performance up to 500°F (260°C).

# **FEATURES**

- Fast cure
- Non-corrosive
- O<sup>2</sup> Sensor Safe
- Low Odor
- Manufactured to meet OEM Specs
- Excellent weatherability in sunlight, rain, snow, ozone or temperature extremes
- Long-life reliability



#### TYPICAL APPLICATIONS

- Valve covers
- Transmission pans
- Gearbox covers
- Differential covers
- Timing gear covers
- Thermostat housings

#### **NOTE**

**Not** recommended for use on components continuously in contact with gasoline.

## **Packaging**

Colors: Black

Size: 5 FL Oz Cartridge, 6.75 Oz Auto Can

#### **CURE TIME**

After skin formation, cure continues inward from the surface. In 24 hours (at room temperature and 50% relative humidity) *Dynatex® DynaPlus* Fast Cure Gasket Maker will cure to a depth of about 2mm. Very deep sections, especially to atmospheric moisture when access restricted, will take longer to cure completely. Cure time is extended at lower humidity levels.

#### **HOW TO USE**

- 1. Remove all previous material from mating surfaces.
- 2. Clean and dry all surfaces with a residuefree solvent, such as *Dynatex® Brake and* Parts Cleaner (P/N 49665).
- 3. Apply a continuous and even bead of silicone to one of the prepared surfaces, and then quickly cover with the other substrate to be bonded.

On exposure to moisture, the freshly applied material will "skin over" in about 25 minutes at room temperature and 50% relative humidity. Any tooling should be completed before this skin forms. The surface is easily tooled with a spatula.

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), Dynatex® DynaPlus Fast Cure Gasket Maker has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

#### **USERS PLEASE READ**

The information and data contained herein is believed to be accurate and reliable; however, it responsibility to determine the user's suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if application, the product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Non-warranty:** Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warrantv is the product meets manufacturing specifications in effect at time of shipment. There is no warranty merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.

**Dynatex** 

a division of SOUDAL

350 Ring Road Elizabethtown, KY 42701 Email: sales@dynatex.net

Toll Free: (800) 999-2937 Ph: (270) 769-5557 Fax (270) 769-6418 Website: www.dynatex.net

143358, 143359/ 04-20 MADE IN U.S.A.